




## Code: 199000005

Description: Glue with solvent base to stick the defleco on the road

1515/15/

istemi / Sicurezz

COLLANTE BITUMINOSC



The base of the defleco must be clean from any traces of adhesives used previously, from dirt and substances extraneous. The road pavement must be clean and clear of non-coherent materials such as stones or gravel.

Consumption: • From 30 to 50 defleco each tan

# Drying and Hardening: • Temperature: Min 5 °C - Max 40°C

# Drying or hardening at 23 ° C and 50% U.R.

- Appearance attachment: 45 minutes
- Set times: 12 h

## Characteristics of the dried product:

Characteristic	Value	Tolerance	U.M.
Elongation at break	1600	± 200	%
Cold flexibility	-25	± 5	°C

## Packaging indications:

- Available colors: Black
- Packaging: 5 kg (net weight 4.75 kg)

## Storage temperature:

- Indications for storage: Min 5 ° C Max 40 ° C
- Stability in original packaging: 24 months

# Features:

SUPER FIX-D is an adhesive consisting of solution bitumen elastomerized with particular macromolecules that make it particularly elastic and dried product. It is used for gluing the defleco on the road.

## Appearance:

Black color tixotropic paste

## Liquid product features:

Characteristic	Value	Tolerance	U.M.
Specific weight	1.11	± 0,05	Kg/dm³
Dry leftover	75	± 1	%

# Application Mode:


SUPER FIX-D must be put on with a brush or a trowel and put a suitable amount of product at the base of the defleco then the user has to put the item on the ground, exerting making a small power, so to permit to the product to stick well on the ground.

## Installation Instructions:

- · Equipment: Brush or Towel
- · Installation instructions: Ready to use
- Type of diluent: /
- Tool cleaning: Dil S1

Via Sputnik, 8

T. +39 (0)75 518641 06073 Ellera Scalo (Pg) **F. +39 (0)75 5173016**  info@sisas.it www.sisas.it





Page 1 of 1

